

NORTHTOWN

Product Data Sheet

Pipe Protection Products

BB-99 VOC

Bituminous Black Pipe Coating

Features

- A tough, durable coating for lasting protection of steel pipe. The pipe coating is effective for both indoor and outdoor storage. Can be applied to new and reconditioned pipe. When applied over light rust it will stop further deterioration. For shop application only. Not for architectural use.

Typical Uses

Excellent exterior durability and adhesion over most metal, wood, and concrete surfaces.

Physical Data

Pencil Hardness (ambient cure)	Soft to 4B	Theoretical volume solids of mixed material	35%±1%
Adhesion (ASTM D 4541)	300 psi	Theoretical coverage of mixed gallon (1 mil)	560 sq. ft.
Temperature resistance (non-immersion)		Volatle Organic Content	
Continuous	250°F	Unthinned ready to apply	3.43 lbs./gal.
Non-continuous	300°F		

Resistance

BB-99 is designed for exposures to mild chemical fumes under typical atmospheric conditions.

Exposure	Immersion	Splash & Spillage	Fumes
Acidic	Not recommended	Poor	Fair
Alkaline	Not recommended	Poor	Fair
Solvents	Not recommended	fair	Good
Salt water	Not recommended	Good	Excellent
Water	Not recommended	Good	Excellent

Film Thickness (per coat)

Dry film thickness: 1.0-2.0 mils
Wet film thickness: 3 - 5 mils
Theoretical coverage: 560 sq. ft. @ 1 mils DFT 330 sq. ft. @ 2 mils DFT.

Primer/Substrates

BB-99 Pipe Coating may be applied directly to properly prepared steel substrates and weathered galvanized steel

Colors

Standard Black High Gloss or Sheen.

Shipping Data

Packaging unit	55 gal.	5 gal.	Flash Point: (Setaflash) BB-99 45°F
Shipping weight (approx.)			Shelf Life: 3 years when stored inside at 40°F to 110°F.
Package unit	400 lbs.	60 lbs.	DOT Classification Paint Flammable liquid UN1263 PG II

Surface Preparation

BB-99 Pipe Coating is designed to be used over surfaces that have been prepared in accordance with SSPC-SP2 Hand Tool Clean specification. In many cases High Pressured Water Blast will suffice.

Mixing

Mix BB-99 Pipe Coating well prior to application.

Thinning

Thinning is not required for most applications; however BB-99 Pipe Coating may be thinned up to 1 pint/gal. CC-107 is recommended for applications. For VOC control thin only with thinner #4.

800-WRAP-A-PIPE

P.O. Box 2064 Huntington Beach CA 92647

714-897-0700 FAX 714-897-0600

NORTHTOWN

Pipe Protection Products

Product Data Sheet

BB-99 Black Bituminous Pipe Coating Product Data Sheet

	<u>Material</u>	<u>Surface</u>	<u>Applications Conditions</u>
Minimum	40°F	40°F	Ambient 40°
Maximum	1200°F	120°F	120°F

Special thinning and application procedures are required outside these temperatures. Surface temperatures should be 5°F above dew point to prevent condensation.

Application Equipment

Conventional Spray: Industrial sprayers such as DeVilbiss MBC or JGA and Binks 18 or 62 having double regulated pressure pot, 3/8" I.D. minimum material hose and a .070" I.D. fluid tip and air cap are recommended.

Airless Spray: Sprayer such as Graco's Bulldog with a 30:1 ratio and a .017" to .021" tip is recommended. A 30 mesh inline filter is recommended.

Brush or Roller: Use medium brush and short nap roller with solvent resistant fibers and core.

Drying Time

The following minimum times are based on 1.5 mils DFT and adequate air ventilation. Higher thickness and reduced air circulation increase drying times.

<u>Surface Temperature</u>	<u>To Touch</u>	<u>To Handle</u>	<u>To Recoat</u>
60°F	3-5 min.	30 min.	over night

Maximum Recoat

BB-99 Pipe Coating can be recoated with itself at any time by simply removing dirt and contamination of the existing coat.

Cleanup

Cleanup spill splatters and equipment using mineral spirits. Lacquer thinner or Thinner #4 for VOC control.

10/30/08

CAUTION: Read and follow all caution statements on this product data sheet and on the Material Safety Data Sheet for this product.

CONTAINS FLAMMABLE SOLVENTS. Vapors are heavier than air and will accumulate. Extinguish all flames and prevent all sparks. All electrical equipment and installations should be made and grounded in accordance with the National Electrical Code. Where explosion hazards exist workers are required to use non-sparking tools and wear non-sparking shoes.

HEALTH: In confined spaces workers must wear fresh airline respirators.

Page 2 of 2

800-WRAP-A-PIPE
P.O. Box 2064 Huntington Beach CA 92647
714-897-0700 FAX 714-897-0600